

The following table is a current statistical average of our Coarse sand

<u>Sieve Number</u>	<u>Average Percent Passing</u>
3/8	100.0
4	96.8
8	89.8
16	78.4
30	57.6
50	7.4
100	0.4
Fineness Modulus	2.70